




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : H01L		A2	(11) International Publication Number: WO 00/46839
			(43) International Publication Date: 10 August 2000 (10.08.00)
(21) International Application Number: PCT/US00/02954 (22) International Filing Date: 4 February 2000 (04.02.00) (30) Priority Data: 60/118,904 5 February 1999 (05.02.99) US (71) Applicant (for all designated States except US): UNIVERSITY OF MARYLAND, BALTIMORE [US/US]; Office of Research & Development, 520 West Lombard Street, Baltimore, MD 21201-1627 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): LAKOWICZ, Joseph, R. [US/US]; 10037 Fox Den Road, Ellicott City, MD 21042 (US). GRYCZYNSKI, Ignacy [PL/US]; 4203 Glenmore Avenue, Baltimore, MD 21206 (US). GRYCZYNSKI, Zygmunt [PL/US]; 4713 Roundhill Road, Ellicott City, MD 21043 (US). (74) Agent: BRUMLIK, Charles, J.; Mathews, Collins, Shepherd & Gould, P.A., Suite 306, 100 Thanet Circle, Princeton, NJ 08540-3674 (US).			(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published Without international search report and to be republished upon receipt of that report.

(54) Title: LUMINESCENCE SPECTRAL PROPERTIES OF CdS NANOPARTICLES

(57) Abstract

The steady state and time resolved luminescence spectral properties of two types of novel CdS nanoparticles and nanoparticles are described. CdS nanoparticles formed in the presence of an amine-terminated dendrimer show blue emission. The emission wavelength of these nanoparticles depended on the excitation wavelength. The CdS/dendrimer nanoparticles display polarized emission with the anisotropy rising progressively from 340 to 420 nm excitation, reaching a maximal anisotropy value in excess of 0.3. A new constant positive polarized emission from luminescent nanoparticles is also described. Polyphosphate-stabilized CdS nanoparticles are described that display a longer wavelength red emission maximum than bulk CdS and display a zero anisotropy for all excitation wavelengths. Both nanoparticles display strongly heterogeneous intensity decays with mean decay times of 93 ns and 10 μ s for the blue and red emitting particles, respectively. Both types of nanoparticles were several times more photostable upon continuous illumination than fluorescein. In spite of the long decay times the nanoparticles are mostly insensitive to dissolved oxygen but are quenched by iodide. These nanoparticles can provide a new class of luminophores for use in chemical sensing, DNA sequencing, high throughput screening and other applications.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

LUMINESCENCE SPECTRAL PROPERTIES OF CdS NANOPARTICLES

5 This patent application claims the benefit of U.S. Provisional Patent Application
Serial No. 60/118,904 dated February 5, 1999.

 The United States Government may have rights to this invention pursuant to the
National Institute of Health (NIH), National Center for Research Resources, Grant
No. RR-08119.

10

FIELD OF THE INVENTION

 This invention relates to nanoparticle cadmium sulfide (CdS) fluorescent probes.
Preferably, this invention relates to CdS nanoparticles formed in the presence of an
amine-terminated dendrimer and/or polyphosphate-stabilized CdS particles both with
15 average diameters or other critical dimensions (CDs) of several nanometers (nm).

BACKGROUND

 There is presently widespread interest in the physical and optical properties of
semiconductor particles with average diameters or CdS measured in nanometers.
20 These particles are often called nanoparticles or quantum dots. The optical
properties of such particles depends on their size [Martin, C.R.; Mitchell, D.T., *Anal.*
Chem. (1998) 322A-327A].

 Such particles display optical and physical properties which are intermediate
between those of the bulk material and those of the isolated molecules. For
25 example, the optical absorption of bulk CdSe typically extends to 690 nm. The

longest absorption band shifts to 530 nm for CdSe nanoparticles with 4 nm average diameters [Bawendi, M.G.; *et al.*, *Annu. Rev. Phys. Chem.* (1990) 41, 477-496].

Sizes of nanoparticles are usually measured by average diameters of equivalent spherical particles. For particles that are not at least approximately spherical, the smallest dimension (called critical dimension or CD) is often used. In nanoparticles a large percentage of the atoms are at the surface, rather than in the bulk phase. Consequently, the chemical and physical properties of the material, such as the melting point or phase transition temperature, are affected by the particle size. Semiconductor nanoparticles can be made from a wide variety of materials including, but not limited to CdS, ZnS, Cd₃P₂, PbS, TiO₂, ZnO, CdSe, silicon, porous silicon, oxidized silicon, and Ga/InN/GaN.

Semiconductor nanoparticles frequently display photoluminescence and sometimes electroluminescence. For example see Dabbousi, B.O., *et al.*, *Appl. Phys. Lett.* (1995) 66(11), 1316-1318; Colvin, V.L., *et al.*, *Nature*, (1994) 370, 354-357; Zhang, L., *et al.*, *J. Phys. Chem. B.* (1997) 101(35), 874-6878; Artemyev, M.V., *et al.*, *J. Appl. Phys.*, (1997) 81(10), 6975-6977; Huang, J., *et al.*, *Appl. Phys. Lett.* (1997) 70(18), 2335-2337; and Artemyev, M.V., *et al.*, *J. Crys. Growth*, (1988) 184/185, 374-376. Additionally, some nanoparticles can form self-assembled arrays.

Nanoparticles are being extensively studied for use in optoelectronic displays. Photophysical studies of nanoparticles have been hindered by the lack of reproducible preparations of homogeneous size. The particle size frequently changes with time following preparation. Particle surface is coated with another semiconductor or other chemical species to stabilize the particle [Correa-Duarte, M.A., *et al.*, *Chem. Phys. Letts.* (1998) 286, 497-501; Hines, M.A., *et al.*, *J. Phys.*

Chem. (1996) 100, 468-471; and Sooklal, K., *et al.*, *J. Phys. Chem.* (1996) 100, 4551-4555].

There are several examples of fluorescing cadmium sulfide nanoparticles. Tata, *et al.* use emulsions [Tata, M., *et al.*, *Colloids and Surfaces*, 127, 39 (1997)].

- 5 Fluorescence of CdS nanocrystals have been observed by low temperature microscopy. Blanton, *et al.* show fluorescence from 5.5 nm diameter CdS nanocrystals with excitation of 800 nm and emission centered around 486 nm [Blanton, S., *et al.*, *Chem. Phys. Letts.*, 229, 317 (1994)]. Tittel, *et al.* noticed fluorescence of CdS nanocrystals by low temperature confocal microscopy [Tittel, J.,
10 *et al.*, *J. Phys. Chem. B*, 101(16) (1997) 3013-3016].

A 64 branch poly(propylene imine) dendritic box can trap a Rose Bengal molecule (*i.e.*, a polyhalogenated tetracyclic carboxylic acid dye) to allow it to strongly fluoresce since it is isolated from surrounding quenching molecules and solvents [Meijer, *et al.*, *Polym. Mater. Sci. Eng.*, (1995) 73, 123].

- 15 While the absorption and emission spectra of nanoparticles have been widely studied, the scope of these measurements were typically limited to using the optical spectra to determine the average size of the particles. There have been relatively few studies of the time-resolved photophysical properties of these particles.

- The emission from silicon nanoparticles has been reported as unpolarized [Brus, 20 L.E., *et al.*, *J. Am. Chem. Soc.* (1995) 117, 2915-2922] or polarized [Andrianov, A.V., *et al.*, *JETP Lett.* (1993) 58, 427-430; Kovalev, D., *et al.*, *Phys. Rev. Letts.* (1997) 79(1), 119-122; and Koch, F., *et al.*, *J. Luminesc.*, (1996) 70, 320-332]. Polarized emission has also been reported for CdSe [Chamarro, M., *et al.*, *Jpn. J. Appl. Phys.* (1995) 34, 12-14; and Bawendi, M.G., *et al.*, *J. Chem. Phys.* (1992) 96(2), 946-954].

However, in these cases the polarization is either negative or becomes negative in a manner suggesting a process occurring within the nanoparticle. Such behavior would not be useful for a fluorescence probe for which the polarization is expected to depend on rotational diffusion.

5 The increasing availability of homogeneous sized nanoparticles suggests more detailed studies of their photophysical properties, which in turn could allow their use as biochemical probes. The first reports of such particles as cellular labels have just appeared [Bruchez, M., *et al.*, *Science* (1998) 281, 2013-2016; and Chan, W., *et al.*, *Science* (1998) 281, 2016-2018]. CdS particles have also been synthesized which
10 bind DNA and display spectral changes upon DNA binding [Mahtab, R., *et al.*, *J. Am. Chem. Soc.* (1996) 118, 7028-7032; and Murphy, C.J., *et al.*, *Proc. Materials Res. Soc.* (1997) 452, 597-600].

U.S. Patent No. 5,938,934 to Balogh, *et al.*, describes use of dendrimers as hosts for many materials including semiconductors. However, the nanoparticles are
15 somewhat large for fluorescence based on size. Only example 15 discloses cadmium sulfide. However, dangerous sulfide gas is used over prolonged periods of time. Fluorescence is mentioned, but not discussed for semiconductors or metal sulfides.

20

SUMMARY

This invention describes fabrication methods, spectroscopy, probes and other applications for semiconductor nanoparticles. The preferred embodiments are two types of cadmium sulfide (CdS) nanoparticles. CdS nanoparticles formed in the presence of an amine-terminated dendrimer show blue emission. The emission

wavelength of these nanoparticles depends on the excitation wavelength. These CdS/dendrimer nanoparticles display a new constant positive polarized blue emission. Polyphosphate-stabilized CdS nanoparticles are described that display a longer wavelength red emission maximum than bulk CdS and display a zero anisotropy for all excitation wavelengths. Both nanoparticles display strongly heterogeneous intensity decays with mean decay times of 93 ns and 10 μ s for the blue and red emitting particles, respectively. Both types of nanoparticles were several times more photostable upon continuous illumination than fluorescein. In spite of the long decay times the nanoparticles are mostly insensitive to dissolved oxygen but are quenched by iodide. These nanoparticles can provide a new class of luminophores for use in chemical sensing, DNA sequencing, high throughput screening, fluorescence polarization immunoassays, time-gated immunoassays, time-resolved immunoassays, enzyme-linked immunosorbent assay (ELISA) assays, filtration testing, and targeted tagging and other applications.

15

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 shows absorption and emission spectra for the blue emitting CdS/dendrimer nanoparticle in methanol at room temperature. The excitation spectrum of this nanoparticles overlaps with the absorption spectrum. Also shown are the excitation and emission anisotropy spectra, also in methanol at room temperature.

20

Figure 2 shows photostability tests of the CdS/dendrimer and polyphosphate-stabilized (PPS) nanoparticles. The sample was contained in a standard 1 cm x cm (4 mL) cuvette. The incident power was 30 mW at 405 nm from a frequency-doubled

Ti:Sapphire laser, 80 MHz, 200 fs, which was focused with a 2 cm focal length lens. Also shown is the intensity from fluorescein, pH 8, under comparable conditions. When illuminated with the output of a 450 W xenon lamp (385 nm for blue and 405 nm for red nanoparticles) there was no observable photobleaching.

5 Figure 3 shows emission spectra of the CdS/dendrimer composite for different excitation wavelengths. Also shown as the dashed line is the transmission profile of the filter used for the time-resolved measurements.

Figure 4 shows a frequency-domain intensity decay of the CdS/dendrimer nanoparticle for excitation at 395 nm (top) and 325 nm (bottom). This solid line
10 shows the best three decay time fit to the data.

Figure 5 shows time-dependent intensity decays of the nanoparticles reconstructed from the frequency-domain data (Tables I and II).

Figure 6 shows a frequency-domain anisotropy decay of the CdS/dendrimer nanoparticle for excitation at 395 nm, at room temperature in methanol.

15 Figure 7 shows absorption (A) and emission (F) spectra of the CdS/PPS nanoparticles. In this case the emission spectra were found to be independent of excitation wavelengths from 325 to 450 nm. The dashed line shows the transmission of the filter used to record the time-resolved data.

Figure 8 shows excitation anisotropy spectra of the CdS/PPS nanoparticles in
20 80% glycerol at -60 °C (dots). Also shown are the temperature dependent spectra in 80% glycerol.

Figure 9 shows a frequency-domain intensity decay of the CdS/PPS nanoparticles for excitation at 442 nm (top) and 325 nm (bottom). The solid lines show the best three decay time fits to the data.

Figure 10 shows the effect of oxygen on the emission spectra of the CdS/dendrimer and CdS/PPS nanoparticles.

Figure 11 shows the effect of acrylamide and iodide on the emission spectra of the CdS/dendrimer and CdS/PPS nanoparticles.

5 Figure 12 shows intensity decays of the CdS/dendrimer (top) and CdS/PPS nanoparticles (bottom) in the absence and presence of 0.2 M acrylamide or 0.2 M iodide. These measurements were done independently of those presented in Figures 4 and 9. For the CdS/dendrimer nanoparticle (top panel) the recovered average lifetimes ($\tau = \sum f_i \tau_i$) are: 106.0 ns for not quenched (\bullet), 73.7 ns in presence
10 of 0.2 M acrylamide (\circ) and 36.7 ns in presence of 0.2 M KI (\blacktriangle). For the CdS/PPS nanoparticles (lower panel) average lifetimes are 9.80 μ s for not quenched (\bullet), 8.45 μ s in presence of 0.2 M acrylamide (not shown), and 4.09 μ s in presence 0.2 M KI (\blacktriangle).

15

DETAILED DESCRIPTION

This invention describes detailed studies of the steady state and time-resolved emission semiconductor nanoparticles. The preferred embodiments are two types of stabilized CdS particles. The first type of CdS nanoparticles were fabricated in the presence of a dendrimer and display blue emission. The second type of CdS
20 particles were stabilized with polyphosphate and display red emission.

Semiconductor nanoparticles with fluoresce and/or luminesce more intensely and often at wavelengths shifted from their bulk counterparts. The nanoparticles of

the present invention luminesce most strongly when they have average diameters and/or critical dimensions less than 5 nm. The nanoparticles of the present invention have a very narrow distribution of diameters and/or critical dimensions. In the preferred mode of this invention, at least 90% of a nanoparticle powder has critical dimensions of no more than +/- 15% from the average diameter and/or critical dimension of the powder. This narrow particle size distribution is extremely important for maximizing emission intensity and other fluorescent properties.

The semiconductor nanoparticles of the present invention may be only one semiconductor, composites of several materials in each nanoparticle, and/or mixtures of different nanoparticles (e.g., powders, agglomerates, and/or aggregates). The individual nanoparticles can be uncoated, coated, partially coated, attached to a molecule, and/or trapped in a nanoscopic volumetric area. In one contemplated example, a semiconductor nanoparticle is coated with another semiconductor. The coating preferably has a higher bandgap than the core nanoparticle. In another contemplated example, electrically non-conductive coatings or anchor molecules control the size and spacing of the semiconductive nanoparticles. Coatings can also be used to protect the core nanoparticle from other effects such as, but not limited to, certain wavelengths, oxidation, quenching, size changes, size distribution broadening, and electronic conductivity. There may be more than one coating layer and/or material.

The nanoparticles of the present invention have at several important improvements. First, the dendrimer-based and other types of template-based nanoparticles show polarized emission. Polarization offers many advantages and an additional variable over prior fluorescent nanoparticle spectroscopy. Second, the

nanoparticles of the present invention are very resistant to quenching by oxygen or other dissolved species. This important advance avoids the quenching problems that plague much of fluorescence spectroscopy. Third, the nanoparticles of the present invention have long wavelength emission. Emission wavelengths of above
5 500 nm possible with the present invention are especially suitable for biological sensing and minimize autofluorescent noise. Fourth, the nanoparticles of the present invention have long lifetimes. Lifetimes of 30 ns to well over 100 ns are possible with this invention even in the presence of fluorescence quenchers. Long lifetimes allow use of smaller and less expensive spectrometers, sensors and
10 detectors. The combination of long lifetimes with long fluorescence decay times are particularly valuable.

This invention's preferred mode describes solution phase nanofabrication of semiconductor nanoparticles. Solution phase nanofabrication is much less expensive than most types of nanofabrication using vacuum systems,
15 electrochemistry, special ball mills, electric arcs, gas phase chemistry, etc. This invention's nanoparticles can be made in bulk or within a template such as, but not limited to, a dendrimer membrane or dendrimer-modified optical fiber. This invention avoids the use of dangerous and expensive reactive gases such as sulfide gas.

20 *CdS/Dendrimer Nanoparticle*

Figure 1 shows the absorption and emission spectra of the CdS/dendrimer particles. There is a substantial Stokes' shift from 330 to 480 nm. Such a large Stokes' shift is a favorable property because the emission of the nanoparticles will be observable without homo-energy transfer between the particles. Also, because of

the substantial shift it should be relatively easy to eliminate scattered light from the detected signal by optical filtering. The term nanoparticle in this invention is meant to include nanocomposites, clusters of nanoparticles, agglomerates of generally electrically isolated nanoparticles and surface-modified nanoparticles as well as
5 single material particles.

The emission intensity of the blue nanoparticles is relatively strong. The relative quantum yield is estimated by comparing the fluorescence intensity with that of a fluorophore of known quantum yield, and an equivalent optical density at the excitation wavelength of 350 nm. A solution of coumarin 1 in ethanol with a reported
10 quantum yield of 0.73 was used as a quantum yield standard. This comparison yields an apparent or a relative quantum yield of 0.097. This value is not a molecular quantum yield because there is no consideration of the molar concentration of the nanoparticles. However, this value does indicate the relative brightness of the particles as compared to a known fluorophore. This value is somewhat lower than
15 the previously reported quantum yield of approximately 0.17 [Murphy, C. J., Brauns, E. B., and Gearheart, L. (1997), Quantum dots as inorganic DNA-binding proteins, *Proc. Materials Res. Soc.* 452, 597-600]. It is possible that the quantum yields differ for different preparations of the nanoparticles.

For use as a luminescent probe the signal from the nanoparticles must be stable
20 with continual illumination. The emission intensities and/or emission spectra of nanoparticles occasionally depend on illumination. In contrast, the CdS/dendrimer particles appear to be reasonably stable and about two-fold more stable than fluorescein (Figure 2). In these stability tests the fluorescein and nanoparticles were illuminated with the focused output of a frequency-doubled Ti:Sapphire laser. No

changes in the emission intensity of the nanoparticles were found when illuminated with the output of a 450W xenon lamp and monochromator.

For use as a biophysical probe of hydrodynamics a luminophore must display polarized emission. Since most nanoparticles are thought to be spherical, the emission is not expected to display any useful polarization. Importantly, the CdS/dendrimer nanoparticles of the present invention display high anisotropy (Figure 1). This anisotropy increases progressively as the excitation wavelength increases across the long wavelengths side of the emission, from 350 to 430 nm. The emission anisotropy is relatively constant across the emission spectra. These properties, and the fact that the anisotropy does not exceed the usual limit of 0.4, suggest that the emission is due to a transition dipole similar to that found in excited organic molecules. The high and non-zero anisotropy also suggests that the excited state dipole is oriented within a fixed direction within the nanoparticles.

A fixed direction for the electronic transition suggests the presence of some molecular features which define a preferred direction for the transition moment. While most nanoparticles are thought to be spherical, the shape of the CdS inside of the CdS/dendrimer nanoparticle is not known. Electron micrographs show that the particles and dendrimers exist as larger aggregates rather than as isolated species. Unfortunately, the presence of aggregates prevented determination of the particle shape. Our observation of a large non-zero anisotropy for these particles suggests an elongated shape for the quantum-confined state. This is the first constant positive polarized emission from CdS nanoparticles. The results in Figure 2 suggest that CdS/dendrimer nanoparticles can serve as hydrodynamic probes for rotational motions on the 50 to 400 ns timescale (see Figure 4 below).

If the particle preparation has a single particle size, the emission spectra are expected to be independent of excitation wavelength. Hence we recorded the emission spectra for the CdS/dendrimer particles for a range of excitation wavelengths (Figure 3). Longer excitation wavelengths results in a progressive shift
5 of the emission spectra to longer wavelengths. This effect is reminiscent of the well-known red edge excitation shift observed for organic fluorophores in polar solvents. However, the molecular origin of the shift seen in Figure 3 is different. In this case the shifts are probably due to the wavelength-dependent excitation of a selected sub-population of the particles at each wavelength. In particular, longer excitation
10 wavelengths probably results in excitation of larger particles with a longer wavelength emission maximum. Hence this particular preparation of CdS/dendrimer particles appears to contain a range of particle sizes. However, we cannot presently exclude other explanations for the wavelength-dependent spectra seen in Figure 3.

We examined the time-resolved intensity decay of the CdS/dendrimer particles
15 using the frequency-domain (FD) method [J.R. Lakowicz and I. Gryczynski, Topic in Fluorescence Spectroscopy, Vol I, Techniques, Plenum Press, New York, pp 293-355]. The frequency responses were found to be complex (Figure 4), indicating a number of widely spaced decay times. The FD data could not be fit to a single or double decay time model (Table I). Three decay times were needed for a
20 reasonable fit to the data, with decay times ranging from 3.1 to 170 ns. The mean decay time is near 117 ns. There seems to be a modest effect of excitation wavelength. The mean decay time decreases from 117 ns for excitation at 395 nm to 93 ns for excitation at 325 nm. Such long decay times are a valuable property for a luminescent probe, particularly one which can be used as an anisotropy probe.

The long decay time allows the anisotropy to be sensitive to motions on a timescale comparable to the mean lifetime. Hence, it is envisioned to use these nanoparticles as probes for the dynamics of large macro molecular structures, or even as model proteins since the nanoparticle size is comparable to the diameter of many proteins.

5 To better visualize the intensity decays, the parameters (α_i and τ_i) recovered from the least-squares analysis in Table I were used to reconstruct the time-dependent intensity decays (Figure 5). The intensity is multi- or non-exponential at early times (insert), but does not display any long-lived microsecond components. While the intensity decay could be fit to three decay times, it is possible that the
10 actual decay is more complex, and might be more accurately represented as a distribution of decay times.

 In the frequency-domain anisotropy decay of the CdS/dendrimer particles (Figure 6), the differential polarized phase angles are rather low, with the largest phase angles centered near 1.0 MHz, suggesting rather long correlation times for the
15 particles. Least squares analysis of the FD anisotropy data revealed a correlation time near 2.4 μ s (Table I). Such a long correlation time is consistent with the observation that the CdS nanoparticles are aggregated with the dendrimers, or somehow present in a composite structure. Much shorter correlation times would be expected for particles with sizes near 2 nm that would be consistent with the optical
20 properties. The time-zero anisotropy recovered from the FD anisotropy data is consistent with that expected from the excitation anisotropy spectra and the excitation wavelength. This agreement suggests that the anisotropy of these particles decays due to overall rotational motion, and not due to internal electronic

properties of the particles. It is envisioned that these nanoparticles (especially when not aggregated) are useful as analogues of proteins or other macromolecules, and as internal cellular markers which could report the rate of rotational diffusion.

Dendrimers are macromolecules such as poly(amidoamine-organosilicon) containing hydrophilic and hydrophobic nanoscopic domains. The dendrimer have a dense star architecture which is a macromolecular structure with chains that branch from a central initiator core. Dendrimers have narrow molecular weight distributions with specific sizes and shapes. The dendrimers grow larger with each generation. For example, a generation 4 dendrimer is smaller than a generation 5 dendrimer. Dendrimers also have highly functional and accessible terminal surfaces. In the preferred embodiment of this invention, this terminal surface has amine which can bind cadmium. In the present invention, each dendrimer preferably holds a plurality of cadmium sulfide or other semiconductor nanoparticles. Creating semiconductor nanoparticles in dendrimer-based nanoscopic molecular sponges and dendrimer-based network materials (e.g., elastomers, plastomer, coatings, films and membranes) are also envisioned. The present invention can any non-conductive system having nanoscopic domains capable of binding a semiconductor. Envisioned examples include, but are not limited to, dendrimers, star polymers, self-assembling polymers, and zeolites.

20 Polyphosphate-Stabilized CdS Nanoparticles

Other CdS nanoparticles in this invention, called CdS/PPS, have surfaces stabilized with polyphosphate (PPS). Absorption and emission spectra of these particles are shown in Figure 7. Compared to the CdS/dendrimer nanoparticles, these stabilized nanoparticles absorbs and emit at much longer wavelengths. Their

average diameter was estimated to be $4 \text{ nm} \pm 15\%$ by transmission electron microscopy. The spectra and intensities were found to be stable with prolonged illumination and at least four-fold more stable than fluorescein (Figure 2). The emission intensity of these red-emitting particles is considerably weaker than the blue particles. The apparent quantum yield of the red particles was measured relative to 4-(dicyanomethylene)-2-methyl-6-(4-dimethylamino-styryl)-4*H*-pyran (DCM) in methanol, with an assumed quantum yield of 0.38. For equivalent optical densities at the excited wavelength of 442 nm, these particles display an apparent quantum yield of 0.015, and are thus less bright than the blue-emitting CdS/dendrimer nanoparticles.

Compared to the blue-emitting nanoparticles, these red emitting particles display simpler properties. The emission spectra are independent of excitation wavelength, suggesting a narrow size distribution. The excitation spectrum (not shown) overlapped with the absorption spectrum. These nanoparticles can be made to have a long wavelength absorption above 480 nm. The absorption and excitation spectra of the CdS/dendrimer particles also appeared to be identical (Figure 1).

Excitation and emission anisotropy spectra of these polyphosphate-stabilized nanoparticles show zero anisotropy for all excitation and emission wavelengths. The zero anisotropy values could be due to rotational diffusion of the particles during these long luminescence decay (below).

However, time-dependent decay of the anisotropy is not detected, as seen from the frequency-domain anisotropy data. The nanoparticles in 80% glycerol at -60°C also show the anisotropies to be zero for excitation from 350 to 475 nm (Figure 8). These results suggest that polarized emission is not a general property of

nanoparticles, but requires special conditions of synthesis or stabilizers.

The frequency-domain intensity decay of the PPS-stabilized nanoparticles is shown in Figure 9. The intensity decay is complex, again requiring at least three decay times to fit the data (Table II). The intensity decay in the time domain is
5 shown in Figure 5. The decay times range from 150 ns to 25.3 μ s, with a mean decay time near 9 μ s. Once again there was an effect of excitation wavelength, but less than seen with the blue-emitting CdS/dendrimer nanoparticles.

Observation of microsecond decay times for these red emitting particles is an important result. There is currently considerable interest in using red or near infrared
10 (NIR) probes for non-invasive and/or in-vivo measurements. Most such probes display relatively short decay times, typically less than 1 ns. While a few metal-ligand complexes are known to emit in the red and to display long lifetimes the choice of probes with long lifetimes are limited. These intensity decay data for the polyphosphate-stabilized nanoparticles suggest that such nanoparticle probes can
15 provide a new class of luminophores with both long wavelength emission and long decay times.

Commonly used quenchers sometimes do not affect nanoparticle emission. The effect of oxygen are shown in Figure 10. Dissolved oxygen had a modest effect on the intensity from the CdS/dendrimer particles, with the emission being quenched by
20 about 40% for equilibration at one atmosphere of oxygen (top). Remarkably, dissolved oxygen had no effect on the emission from the CdS/PPS particles (lower panel). This is particularly surprising given the long intensity decay time of these particles. The absence of quenching by oxygen could be a valuable result. For instance, the absence of oxygen quenching is a valuable property of the lanthanides,

allowing long decay times in samples exposed to air. These results suggest that some nanoparticles may be insensitive to oxygen, and thus useful for high sensitivity gated detection as is used in the lanthanide-based immunoassays. The CdS/dendrimer nanoparticles were quenched by both iodide and acrylamide (Figure 11, top). The CdS/PPS particles were quenched by iodide but not significantly by acrylamide (bottom). The quenching observed for both types of nanoparticles seems to be at least partially dynamic, as seen by the decrease in mean decay time (Table III).

Many potential applications of nanoparticles as luminescent probes are envisioned. Red-NIR emitting probes with long decay times and optionally resistance to oxygen quenching are envisioned. A favorable property of the nanoparticles is the long intensity decay times. This allows those particles which display anisotropy to be used in hydrodynamic probes on the timescales ranging from hundreds of nanoseconds to microseconds. This is a timescale not usually available to fluorescence without the use of specialized luminophores. The luminescence decay times can be adjusted by changes in nanoparticles and nanoparticle composition, morphology, size, shape and surface modifications.

It is envisioned that the nanoparticles of the present invention could display resonance energy transfer. For example, the nanoparticles could display resonance energy transfer to absorbing dyes or could display Förster transfer.

Sensors incorporating the nanoparticles of the present invention are also envisioned for chemical, biological, optical and other applications. Preferred embodiments are sensors for important species such as Ca^{2+} , pH and/or chloride. Attachment of analyte-dependent absorbers to the nanoparticles are envisioned for

analyte-dependent emission.

Preferred methods of making the nanoparticles of the present invention are described in Examples 1-2. Preferred methods of spectroscopic measurements of the nanoparticles of the present invention are described in Example 3.

5

EXAMPLE 1
Nanofabrication of CdS/dendrimer Nanoparticles

The blue emitting CdS particles were prepared in the presence of poly(aminoamine) STARBURST® dendrimer, generation 4.0 (Dow Corning, Midland, MI; Dendritech™, Inc., Midland, MI; Michigan Molecular Institute, Midland, MI; Aldrich, Allentown, PA). The STARBURST® dendrimer (PAMAM) of generation 4.0 was purchased from Aldrich. This dendrimer is expected to have 64 surface amino groups. Based on the manufacturer's value of the dendrimer weight fractions in methanol, and the known dendrimer densities, we prepared dendrimer stock solutions of 1.14×10^{-4} M in methanol under a N₂ atmosphere at 10 °C. The 2.0 mM stock solutions of Cd²⁺ and S²⁻ were prepared by dissolving 62 mg of Cd(NO₃)₂•4H₂O (Baker) in 100 mL of methanol, and by dissolving 15 mg Na₂S (Alfa) in 100 mL of methanol. The Cd²⁺ and S²⁻ stock solutions were freshly prepared. In the standard incremental addition procedure, an 0.50 mL aliquot of Cd²⁺ stock solution was added to 10 mL of the dendrimer stock solution at 10 °C, followed by addition of an 0.50 mL aliquot of S²⁻ stock solution. The Cd²⁺ and S²⁻ additions were repeated 10 times. The resulting solution was colorless and glowed bright blue under UV illumination. The product was stored in a freezer and did not show any

evidence of precipitation for months. This nanoparticle dendrimer composite was stable for long periods of time in neutral methanol.

EXAMPLE 2

Nanofabrication of CdS/PPS Nanoparticles

The red emitting particles are also composed of CdS, but stabilized with polyphosphate [Mahtab, R., Rogers, J. P., and Murphy, C. J. (1995), Protein-sized quantum dot luminescence can distinguish between "straight", "bent," and "kinked" oligonucleotides, *J. Am. Chem. Soc.* 117, 9099-9100]. For the polyphosphate-stabilized (PPS) CdS/PPS nanoparticles, 2×10^{-4} M $\text{Cd}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ in degassed water was mixed with an equivalent amount of sodium polyphosphate, $\text{Na}_6(\text{PO}_3)_6$. Solid Na_2S was added, with vigorous stirring, to yield 2×10^{-4} M sulfide. The solution immediately turned yellow. Under UV light, the solution glowed red-orange.

EXAMPLE 3

Spectroscopic Measurements

Frequency-domain (FD) intensity and anisotropy decays were measured with a fluorescence spectrometer and standard fluorescence techniques [J.R. Lakowicz and I. Gryczynski, *Topic in Fluorescence Spectroscopy*, Vol I, Techniques, Plenum Press, New York, pp 293-355]. The excitation source was a HeCd laser with an emission wavelength of 325 nm or 442 nm. The continuous output of this laser was amplitude modulated with a Pockels' cell. The FD data were interpreted in terms of the multi-exponential model:

$$I(t) = \sum_i \alpha_i \exp (-t / \tau_i) \quad (1)$$

where α_i are the pre-exponential factors and τ_i are the decay times. The fractional contribution of each decay time component to the steady state emission is given by

$$f_i = (\alpha_i \tau_i) / (\sum_j \alpha_j \tau_j) \quad (2)$$

Frequency-domain anisotropy decay data were measured and analyzed as described previously [Lakowicz, J. R., Cherek, H., Kusba, J., Gryczynski, I., and Johnson, M. L. (1993), Review of fluorescence anisotropy decay analysis by frequency-domain fluorescence spectroscopy, *J. Fluoresc.* 3, 103-116] in terms of multiple correlation times:

$$r(t) = \sum_k r_{0k} \exp (-t / \theta_k) \quad (3)$$

In this expression r_{0k} is the fractional anisotropy amplitude which decays with a correlation time θ_k .

The foregoing examples are illustrative embodiments of the invention and are merely exemplary. A person skilled in the art may make variations and modification without departing from the spirit and scope of the invention. All such modifications and variations are intended to be included within the scope of the invention as described in this specification and the appended claims.

Table I. Frequency-domain intensity and anisotropy decays of the CdS/dendrimer nanoparticles

Exc. (nm)	n^a	τ (ns)	α_i	f_i	X^2_R
395	1	61.8	1.0	1.0	1,136.9
	2	6.2	0.747	0.137	
		116.0	0.253	0.863	32.0
	3	3.1	0.748	0.090	
		50.2	0.163	0.319	
		169.8	0.089	0.591	1.1
325	1	52.3	1.0	1.0	991.5
	2	7.8	0.705	0.160	
		97.9	0.295	0.890	37.5
	3	2.7	0.699	0.080	
		39.5	0.205	0.341	
		142.8	0.096	0.579	1.7

^a Number of exponents

- 5 At an excitation of 395 nm and an n^a of 1, the following anisotropy decay values are seen: $\theta_k = 2,430.5$ ns; $r_{0k} = 0.228$; and $X^2_R = 0.6$

Table II. Frequency-domain intensity decay of the Cd²⁺ enriched nanoparticles

Exc. (nm)	n ^a	τ (ns)	α_i	f_i	X^2_R
442	1	597.50	1.00	1.00	1,656
	2	290.40	0.932	0.448	
		4,907	0.068	0.552	242.90
	3	150.00	0.749	0.188	
		1,171	0.243	0.476	
		25,320	0.008	0.336	2.70
325	1	680.20	1.00	1.00	1212.30
	2	425.00	0.932	0.474	
		6,471	0.068	0.526	93.50
	3	241.60	0.717	0.227	
		1,173	0.273	0.421	
		27,783	0.010	0.352	2.90

^a Number of exponents

Table III. Intensity decay of the nanoparticles with and without quenchers.

Compound/ Conditions	τ (avgas) (ns)	α_1	τ_1 (ns)	α_2	τ_2 (ns)	α_3	τ_3 (ns)	X^2_R
blue, no quencher	106.0	0.698	4.91	0.256	57.7	0.046	214.2	2.2
blue + 0.2 M acrylamide	73.7	0.737	1.07	0.190	18.0	0.073	105.9	4.2
blue + 0.2 M iodide	36.7	0.786	1.11	0.175	11.2	0.039	67.3	4.6
red, no quencher	9.80	0.652	232.5	0.337	1073.3	0.011	2580	3.8
red + 0.2 M acrylamide	8.54	0.761	229.3	0.229	1173.0	0.010	2349	1.9
red + 0.2 M iodide	4.09	0.738	56.3	0.243	673.7	0.019	858.2	3.2

5 ^b The excitation was 325 nm. The emission filter for the blue particles was an interference filter 500 +/- 20 nm. The emission filter for the red particles was a long pass filter at 580 nm.

^c $\tau(\text{avgas}) = \sum_i f_i \tau(\text{avgas})_i$; $f_i = \alpha_i \tau_i / (\sum_i \alpha_i \tau_i)$

We claim:

1. A nanoparticle, comprising:
a semiconductor, capable of fluorescing,
wherein the nanoparticle has an average diameter less than 5 nm, and
5 wherein the nanoparticle is size-stabilized.
2. A nanoparticle according to claim 1, further comprising:
a coating, partial coating, or molecule on the surface of the semiconductor.
3. A nanoparticle, according to claim 1, wherein the semiconductor is cadmium sulfide.
- 10 4. A nanoparticle, according to claim 2, wherein the coating, partial coating, or molecule is essentially non-fluorescing.
5. A nanoparticle, according to claim 2, wherein the coating, partial coating, or molecule is polyphosphate.
6. A nanoparticle according to claim 2, wherein the nanoparticle is part of a
15 composite.
7. A nanoparticle according to claim 6, wherein the composite comprises a dendrimer and a semiconductor nanoparticle.
8. A nanoparticle, according to claim 7, wherein the dendrimer is a generation 4 poly(aminoamine) STARBURST[®] dendrimer.
- 20 9. A nanoparticle according to claim 1, wherein the nanoparticle is capable of constant positive polarized emission.
10. A nanoparticle according to claim 8, wherein the semiconductor comprises cadmium sulfide.
11. A nanoparticle according to claim 1, wherein the semiconductor is at least

one member selected from the group consisting of CdS, ZnS, Cd₃P₂, PbS, TiO₂, ZnO, CdSe, silicon, porous silicon, oxidized silicon, and Ga/InN/GaN.

12. A nanoparticle according to claim 1, wherein the nanoparticle comprises more than one semiconductor.

5 13. A nanoparticle according to claim 2, wherein the nanoparticle comprises more than one non-conducting molecule.

14. A nanoparticle according to claim 13, wherein a plurality of the nanoparticles are bound to the non-conductive molecule which is at least one member selected from the group consisting of a dendrimer, a dendrimer-based nanoscopic molecular sponge, a dendrimer-based network material, a
10 dendrimer-based elastomer, a dendrimer-based plastomer, a dendrimer-based coating, a dendrimer-based film and a dendrimer-based membrane.

15. A powder, capable of fluorescing, comprising:
a plurality of semiconductor particles having an average critical dimension
15 within the range of approximately 2 nm to less than 5 nm,
wherein the majority of the plurality of semiconductor nanoparticles have a size distribution within approximately +/- 15% of the average critical dimension; and
a molecule, coating, or partial coating bound to the surface of the plurality of
20 semiconductor nanoparticles.

16. A powder according to claim 15, wherein the semiconductor is cadmium sulfide.

17. A powder according to claim 15, wherein the molecule is polyphosphate.

18. A powder according to claim 17, wherein the molecule is a dendrimer.

19. A powder according to claim 18, wherein the dendrimer is a generation 4 poly(aminoamine) STARBURST® dendrimer.
20. A powder according to claim 15, wherein the plurality of semiconductor nanoparticles comprise a mixture of at least two semiconductors.
- 5 21. A powder according to claim 15, wherein the non-conducting molecule consists of a plurality of non-conducting molecules.
22. A powder according to claim 15, wherein a majority of the plurality of semiconductor nanoparticles are electrically isolated from each other.
23. A powder according to claim 15, wherein at least part of the plurality of nanoparticles comprise a cluster or an aggregate.
- 10 24. A composite, comprising:
a semiconductor nanoparticle capable of fluorescing
wherein the nanoparticle has an average diameter of approximately 2 to less than 5 nm; and
15 an electrically non-conductive host with nanoscopic domains bound to the surface of the semiconductor,
wherein the host is at least partially transparent to ultraviolet and visible light.
25. A composite according to claim 24, wherein the semiconductor particle is cadmium sulfide; and the host is at least one member selected from the group consisting of a star polymer, a self-assembling polymer, and a zeolite.
- 20 26. A composition, comprising a nanoparticle according to claim 1 and a solvent.
27. A process for making a nanoparticle according to claim 2, wherein:
a $\text{Cd}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ solution is mixed with a molar equivalent solution of

$\text{Na}_6(\text{PO}_3)_6$,

followed by addition and vigorous stirring of Na_2S

in a deoxygenated environment to create the nanoparticle.

28. A process for making a nanoparticle according to claim 10, wherein:

5 a dendrimer solution is mixed with a Cd^{2+} solution and a S^{2-} solution in a deoxygenated environment to create the nanoparticle.

29. A nanoparticle according to claim 7, wherein the fluorescing is polarized.

30. A nanoparticle according to claim 1, wherein the fluorescing is not significantly quenched by oxygen or other dissolved species.

10 31. A nanoparticle according to claim 1, wherein the fluorescing has a long wavelength emission and a long decay lifetime.

32. A nanoparticle according to claim 1, wherein the long wavelength emission is above 500 nm and the lifetime is greater than 30 ns.

15 33. A sensor measuring a concentration of an analyte or the absence thereof in a sample, comprising:

a probe comprising a nanoparticle according to claim 1 capable of emitting a fluorescent signal;

a light source capable of illuminating the probe with light;

a filter capable of rejecting light based on at least one of wavelength or time;

20 an optical detector capable of detecting the fluorescent signal; and

a fluorescence decay time measurement system capable of determining a fluorescence lifetime from the fluorescent signal;

a data analysis system capable of converting the fluorescence lifetime to a concentration value for analyte; and wherein the sensor may be used for at

least one application selected from the group consisting of fluorescence polarization immunoassays, time-gated immunoassays, time-resolved immunoassays, ELISA assays, DNA sequencing, high throughput screening, filtration testing, and targeted tagging.

- 5 34. A method according to claim 33 wherein the nanoparticle is carried by an aerosol.
35. A nanoparticle according to claim 2, wherein the coating is semiconducting, and the coating is a different material than the semiconductor.

1/12






FIG. 1


2/12

**FIG. 2**


3/12

**FIG. 3**


4/12

**FIG. 4**

5/12

**FIG. 5**

6/12

**FIG. 6**

7/12




FIG. 7

8/12






FIG. 8


9/12

**FIG. 9**

10/12

**FIG. 10**

11/12

**FIG. 11**

12/12




FIG. 12

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 August 2000 (10.08.2000)

PCT

(10) International Publication Number
WO 00/46839 A3

- (51) International Patent Classification⁷: **C08K 5/46**, 5/23, 3/10, 3/08, 3/18, C08L 77/00, C08F 283/04, 283/00, G01N 21/00, 21/76, 33/543, 33/551, 33/544, C01B 13/14, C25D 5/02, 7/12, H01L 29/06, 35/24
- (21) International Application Number: PCT/US00/02954
- (22) International Filing Date: 4 February 2000 (04.02.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/118,904 5 February 1999 (05.02.1999) US
- (71) Applicant (*for all designated States except US*): **UNIVERSITY OF MARYLAND, BALTIMORE** [US/US]; Office of Research & Development, 520 West Lombard Street, Baltimore, MD 21201-1627 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **LAKOWICZ, Joseph, R.** [US/US]; 10037 Fox Den Road, Ellicott City, MD 21042 (US). **GRYCZYNSKI, Ignacy** [PL/US]; 4203 Glenmore Avenue, Baltimore, MD 21206 (US). **GRYCZYNSKI, Zygmunt** [PL/US]; 4713 Roundhill Road, Ellicott City, MD 21043 (US).
- (74) Agent: **BRUMLIK, Charles, J.**; Mathews, Collins, Shepherd & Gould, P.A., Suite 306, 100 Thanet Circle, Princeton, NJ 08540-3674 (US).
- (81) Designated States (*national*): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— With international search report.
- (88) Date of publication of the international search report:
30 November 2000
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: LUMINESCENCE SPECTRAL PROPERTIES OF CdS NANOPARTICLES

(57) Abstract: The steady state and time resolved luminescence spectral properties of two types of novel CdS nanoparticles and nanoparticles are described. CdS nanoparticles formed in the presence of an amine-terminated dendrimer show blue emission. The emission wavelength of these nanoparticles depended on the excitation wavelength. The CdS/dendrimer nanoparticles display polarized emission with the anisotropy rising progressively from 340 to 420 nm excitation, reaching a maximal anisotropy value in excess of 0.3. A new constant positive polarized emission from luminescent nanoparticles is also described. Polyphosphate-stabilized CdS nanoparticles are described that display a longer wavelength red emission maximum than bulk CdS and display a zero anisotropy for all excitation wavelengths. Both nanoparticles display strongly heterogeneous intensity decays with mean decay times of 93 ns and 10 μ s for the blue and red emitting particles, respectively. Both types of nanoparticles were several times more photostable upon continuous illumination than fluorescein. In spite of the long decay times the nanoparticles are mostly insensitive to dissolved oxygen but are quenched by iodide. These nanoparticles can provide a new class of luminophores for use in chemical sensing, DNA sequencing, high throughput screening and other applications.

WO 00/46839 A3

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US00/02954

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : Please See Extra Sheet.

US CL : Please See Extra Sheet.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 524/83, 190, 413, 430, 440; 525/420, 431, 477, 540; 436/523, 524, 528, 164, 172; 423/592; 205/123, 157; 257/22, 37, 40

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EAST, WEST

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5,690,807 A (CLARK Jr. et al.) 25 November 1997, col. 2, line 63-col. 3, line 57.	1-35
Y	US 5,434,878 A (LAWANDY) 18 July 1995, col. 3, line 26-col. 4, line 15.	1-35
Y	US 5,525,377 A (GALLAGHER et al.) 11 June 1996, col. 1, line 10-col. 3, line 44.	1-35
Y,P	US 6,048,616 A (GALLAGHER et al.) 11 April 2000, col. 3, line 10-col. 3, line 43.	1-35
Y,P	US 5,938,934 A (BALOGH et al.) 17 August 1999, col. 2, line 55-col. 3, line 65.	1-35

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*G* document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

16 JUNE 2000

Date of mailing of the international search report

30 AUG 2000

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

PENSEE T. DO

Telephone No. (703) 308-0196

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/02954**Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)**

This international report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

Please See Extra Sheet.

1. ☒ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

☐

The additional search fees were accompanied by the applicant's protest.

☒

No protest accompanied the payment of additional search fees.

A. CLASSIFICATION OF SUBJECT MATTER:

IPC (7):

C08K 5/46, 5/23, 3/10, 3/08, 3/18; C08L 77/00; C08F 283/04, 283/00; G01N 21/00, 21/76, 33/543, 33/551, 33/544;
C01B 13/14; C25D 5/02, 7/12; H01L 29/06, 35/24

A. CLASSIFICATION OF SUBJECT MATTER:

US CL :

524/83, 190, 413, 430, 440; 525/420, 431, 477, 540; 436/523, 524, 528, 164, 172; 423/592; 205/123, 157; 257/22,
37, 40

BOX II. OBSERVATIONS WHERE UNITY OF INVENTION WAS LACKING

This ISA found multiple inventions as follows:

This application contains the following inventions or groups of inventions which are not so linked as to form a single inventive concept under PCT Rule 13.1. In order for all inventions to be searched, the appropriate additional search fees must be paid.

Group I, claim(s) 1-14, 26-33 and 35, drawn to nanoparticles, a process of making the particles, a process of using the particles, and an apparatus for using the particles.

Group II, claim(s) 15-23, drawn to a powder capable of fluorescing.

Group III, claim(s) 24 and 25, drawn to a composite.

The inventions listed as Groups I-III do not relate to a single inventive concept under PCT Rule 13.1 because, under PCT Rule 13.2, they lack the same or corresponding special technical features for the following reasons: according to PCT Rule 13.1, applicant is entitled to one product, one process of making the product, one process of using the product and one apparatus of using the product. However, groups I-III are drawn to three different products which lack the same special technical features such as in group II, the powder contains a fluorescing capability while the nanoparticles of group I is composed of a different texture from that of group II, particles vs. powder, and does not require the ability to fluoresce. Group III is a composite which contains an electrically non-conductive host with nanoscopic domains bound to the surface of the semiconductor, a feature which the other two groups lack.